

KERACOLOR FF

High performance, polymer-modified, water-repellent, cementitious grout with DropEffect® and mould-resistant BioBlock technology for joints up to 6 mm



CLASSIFICATION IN COMPLIANCE WITH AS ISO 13007-3

Keracolor FF is an improved (2) cementitious (C) grout (G), with reduced water absorption (W) and high abrasion resistance (A), classified as CG2WA.

WHERE TO USE

Grouting interior and exterior floor and wall tiling (single-fired, double-fired, klinker, porcelain tile, etc.), stone material (natural stones, marble, granite, agglomerates, etc.), glass and marble mosaics.

Some application examples

- Grouting floor and wall ceramic and stone tiles.
- Grouting swimming pools.
- Grouting particularly smooth and glossy floor surfaces (smooth and polished porcelain, pre-smoothened and polished marble, glazed tiles).
- Grouting ceramic tile industrial flooring where resistance to chemical agents is not required (garages, warehouses, etc.).

TECHNICAL CHARACTERISTICS

Keracolor FF is a blend of cement, very fine-graded aggregates, special polymers, additives and pigments. The use of special hydrophobic additives (DropEffect® technology) gives the grouting mortar highly water-repellent properties, making it less prone to dirtiness and with excellent durability. BioBlock consists of special organic molecules which, by distributing themselves evenly in the microstructure of the joints, block the formation of micro-organisms that cause mould damage. It is a product with very low emission of volatile organic compounds, classified as Emission Code ECI Plus by GEV.

The following features are obtained when mixed with the right water ratio and used correctly:

- water-repellent and droplet-effect;
- mould resistant;
- good compressive and flexural strength, good resistance to freeze/thaw cycles, and therefore good durability;
- a smooth final surface with low water absorption, therefore easy to clean;
- very good abrasion resistance;
- low shrinkage, therefore absence of cracks and fissures;
- good resistance to acids with pH >3;

- excellent value for performance.

When mixing **Keracolor FF** with **Fugolastic**, a special synthetic resin-based polymeric additive, the final characteristics are improved providing better durability under harsh conditions (grouting façades, swimming pools, bathrooms, floors with heavy traffic). For further information consult the **Fugolastic** technical data sheet.

RECOMMENDATIONS

- Do not mix **Keracolor FF** with cement or any other products. Never add water to the mixture that is beginning to set.
- Do not blend different colours of grout together as there is a risk of colour inconsistency and lack of uniformity of the final shade once the grout has set.
- Never mix **Keracolor FF** with salty or dirty water.
- Use the product in temperatures between +5°C and +35°C.
- The amount of mix water must be precisely measured. Excess water could induce the appearance of a whitish coat over the surface (efflorescence). Different colour tones could result if mixtures with different water ratios are prepared. Efflorescence over the surface is due to the formation of calcium carbonate and could also be caused by residual moisture contained in adhesives, not fully hydrated grouts, in substrates not adequately dried, or in substrates not adequately protected from rising damp.
- After filling the joints, do not sprinkle **Keracolor FF** powder onto the grout as this can cause uneven colour and reduce the mechanical strength.
- Expansion joints and movement joints in floors and walls should never be filled with **Keracolor FF**, but with the appropriate flexible MAPEI sealant.
- The surface of some ceramic tiles or stone materials are rough or contain micro-porosities. It is recommended to carry out a sample test to verify cleanability and when necessary, apply a protective treatment over the surface, but avoiding penetration into the joints.
- When resistance to acids, high hygienic requirements, or sterile conditions are needed, or for swimming pools and spas with pool water treatment chemicals or cycles that are potentially harmful to cementitious products, use a suitable epoxy grout from the **Kerapoxy** range.

APPLICATION PROCEDURE

Preparing the joints

Before grouting, wait until the installation mortar or the adhesive has completely hardened. Verify that the waiting time indicated on the relevant technical data sheet has elapsed.

The joints must be clean, free of dust and raked back to at least 2/3 of the tile thickness. Excess adhesive or mortar should be removed whilst still fresh.

Wet the joints with clean water when using very porous ceramic tiles in high temperatures and in the presence of wind.

Preparing the mix

While stirring, pour **Keracolor FF** into a clean, rust-free container containing 25 - 29% by weight, dependant on grout colour, of clean water or **Fugolastic** (if required in the application). When grouting floors, the mixture can be made thinner by adding more water (approx. 27 - 30% by weight).

Mix with a low speed mixer to avoid excess formation of air bubbles, to a smooth consistency. Wait 2-3 minutes and briefly re-stir before use. Use the mixture within 2 hours of preparation.

Applying the grout

Fill the joints completely with **Keracolor FF** using the appropriate MAPEI float or rubber squeege, making sure the joints are completely compacted, with no unevenness. Remove excess **Keracolor FF**, while still fresh, from the surface moving the float diagonally across joints.

Finishing

When the mixture loses its plasticity and becomes matt, usually after 10-20 minutes, clean excess **Keracolor FF** with a damp hard cellulose sponge (e.g. MAPEI sponge) working diagonally to the joints. Rinse the sponge frequently using two separate buckets of water: one to remove the excess from the sponge and the other with clean water for rinsing out the sponge. Cleaning can also be carried out with a power float. To aid removal of the

hardened product from the tiles, use a dampened Scotch-Brite® pad or a disc-type power float with special abrasive-felt discs.

If cleaning is carried out too early (when the mixture is still plastic), the grout may be dragged from the joint leading to colour variation. On the other hand, if the grout has already hardened, it is necessary to clean the surface mechanically, which could scratch the surface of the tiles.

When applying **Keracolor FF** in extremely hot, dry or windy climates, it is recommended to wet the joints after several hours. Wet curing of **Keracolor FF** always improves its final performance.

Any residual powdery haze can be cleaned from the surface with a clean dry cloth. After the final cleaning, if the surface of the floors or walls are still contaminated with cementitious resid an acid cleaner can be used (e.g. **UltraCare Keranet**), when the grout is completely cured. If a product to remove grout residues at the time of application is required, the use of **UltraCare Keranet Easy**, suitable to remove excess grout from surfaces immediately after application, is recommended. For the use of products from the **UltraCare** range, please refer to the relative Technical Data Sheets.



Application of Keracolor FF with MAPEI float



Cleaning and finishing joints with a hard cellulose sponge



Floor grouted with Keracolor FF

SET TO LIGHT FOOT TRAFFIC

Floors are set to light foot traffic after approximately 24 hours.

READY FOR USE

(with hypothetical curing at +23°C and 50% R-H.)

Floors are ready for use after approx. 3 days. The grout can be immersed in water after 7 days from grouting.

CLEANING

Clean tools and containers with plenty of water before **Keracolor FF** hardens.

CONSUMPTION

Consumption of **Keracolor FF** varies depending on the width of the joints, the size and thickness of the tiles. Please refer to the product calculator to estimate consumption rates at www.mapei.com.au Some examples of coverage in kg/m² are shown in the chart overleaf.

PACKAGING

20 kg bags and boxes containing 2 kg and 5 kg Alupaks depending on the colour.

COLOURS

Keracolor FF is available in 14 colours from the MAPEI range.

Keracolor FF		
100	WHITE	
103	MOON WHITE	
111	SILVER GREY	
110	MANHATTAN 2000	
112	MEDIUM GREY	
113	CEMENT GREY	
114	ANTHRACITE	
119	LONDAON GREY	
120	BLACK	
130	JASMINE	
132	BEIGE 2000	
133	SAND	
134	SILK	
170	CROCUS BLUE	

N.B.: Due to the printing processes involved, the colours should be taken as merely indicative of the shades of the actual product

STORAGE

Keracolor FF can be stored 12 months as for 20 kg bags and 24 months as for 5 kg bags and 2 kg alu bags in a dry place in original packaging. Always refer to what is written in the packaging.

SAFETY INSTRUCTIONS FOR THE PREPARATION AND INSTALLATION

Instructions for the safe use of our products can be found on the latest version of the Safety Data Sheet, available from our website www.mapei.com.au
 PRODUCT FOR PROFESSIONAL USE.

TECHNICAL DATA (typical values)

In compliance with:

- European EN 13888 as CG2WA
- AS ISO 13007.3 as CG2WA

PRODUCT IDENTITY

Type:	fine powder
Colour:	14 colours from the MAPEI range
Bulk density:	1,000-1,400 kg/m ³
Dry solids content:	100%
EMICODE:	EC1 Plus - very low emission

APPLICATION DATA (at +23°C and 50% R.H.)

Mixing ratio:	100 parts of Keracolor FF with 25-29 parts of water by weight depending on the colour
Consistency of mix:	fluid paste
Density of the mix:	2.0 kg/m ³
pH of mix:	approx. 13
Pot life of mix:	approx. 2 hours
Application temperature:	from +5°C to +35°C
Grouting after installation: – on walls bonded with normal setting adhesive: – on walls bonded with fast setting adhesive: – on walls bonded with mortar: – on floors bonded with normal setting adhesive: – on floors bonded with fast setting adhesive: – on floors laid with mortar:	4-8 hours 1-2 hours 2-3 days 24 hours 3-4 hours 7-10 days
Waiting time for finishing:	10-20 minutes
Set to light foot traffic:	24 hours
Ready for use:	3 days (7 days for water immersion)

FINAL PERFORMANCE

Flexural strength after 28 days: Compressive strength after 28 days: Flexural strength after freeze-thaw cycles: Compressive strength after freeze-thaw cycles: Abrasion resistance: Shrinkage: Water absorption after 30 min.: Water absorption after 4 hours:	In compliance with Australia Standard AS ISO 13007.3 as CG2WA
Resistance to moisture:	excellent
Resistance to ageing:	excellent

Resistance to solvents, oils and alkalis:	excellent
Resistance to acids:	good if pH > 3
Resistance to temperature:	from -30°C to +80°C

CONSUMPTION TABLE DEPENDING ON THE SIZE OF THE TILE AND WIDTH OF THE JOINTS (kg/m²)

Size of the tile (mm)	Width of the joint (mm)		
	2	3	5
75x150x6	0.4	0.5	0.9
100x100x7	0.4	0.6	1.1
100x100x9	0.5	0.8	1.4
150x150x6	0.2	0.4	0.6
200x200x7	0.2	0.3	0.5
200x200x9	0.3	0.4	0.7
300x300x10		0.3	0.5
300x300x20		0.6	1.0
300x600x10		0.2	0.4
400x400x10		0.2	0.4
500x500x10			0.3
600x600x10			0.3
750x750x10			0.2
100x600x9			0.8
150x600x9			0.6
150x900x9			0.5
150x1200x10			0.6
225x450x9			0.5
225x900x9			0.4
250x900x9			0.3
250x1200x10			0.4
600x600x5			0.1
600x600x3			0.1

CONSUMPTION CALCULATION FORMULA:

$$\frac{(A + B)}{(A \times B)} \times C \times D \times 1.5 = \frac{\text{kg}}{\text{m}^2}$$

A = length of tile (in mm)
 B = width of the tile (in mm)
 C = thickness of the tile (in mm)
 D = width of the joint (in mm)

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our website www.mapei.com.au

LEGAL NOTICE

The contents of this Technical Data Sheet (“TDS”) may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in force at the time of the MAPEI product installation.

The most up-to-date TDS can be downloaded from our website www.mapei.com.au

ANY ALTERATION TO THE WORDING OR REQUIREMENTS CONTAINED OR DERIVED FROM THIS TDS EXCLUDES THE RESPONSIBILITY OF MAPEI.

Mapei Australia Pty Ltd

180 Viking Drive, Wacol, Queensland, 4076

 +61 7 3276 5000  www.mapei.com.au  sales@mapei.com.au

131-2-2025 en-au (AU)

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution

