

SILCOR[®] Top Coat 75

Two-Part UV Resistant Protective Coating

Product Description

A tough, fast curing, non-slip, aliphatic polyurethane coating designed for protection of SILCOR[®] membrane systems in all exposed situations. SILCOR Top Coat 75 is UV resistant - it provides a durable, service foot-trafficable finish to roof and deck areas.

Uses

SILCOR Top Coat 75 is used for colour-fast, non-slip exposed areas on plant room and lift motor room roofs, balconies, decks, perimeter turn-ups, penetrations and sill or window flashings.

It may be used to give colour fast protection to all grades of SILCOR waterproof membranes used in exposed external situations.

Features

- Simple application, easy to use and fast cure UV Resistant and foot trafficable
- Fast Cure - Quick access for trades Permanently flexible - total adhesion Immediate Resistance to rain damage

Preparation

Surface of SILCOR membrane must be clean and dry.

Application

Mix each component separately with a clean stirrer blade, then combine together in a clean dry container and mix thoroughly with high speed dissolver for 5 minutes prior to application. Mix ratio Resin: Hardener is 5:1 by weight. Apply in two coats by brush or roller – apply second coat in cross direction to the first to give a uniform finish. For spraying use a single wet-on-wet spray application.

Do not use mixed product once it has become thick and stringy, it should be discarded.

Do NOT add solvent.

Typical Properties

Drying Time @ 25°C	2 hours
Shore Hardness	75-80° A
Tensile Strength (AS1145)	2 MPa
UV Resistance (System)	Excellent

Coverage

SILCOR Top Coat 75 A/B mixed – minimum 0.3kg/m² for minimum 0.15mm Dry Film Thickness (DFT).

Packaging

SILCOR Top Coat 75 Resin – 15 kg pails
SILCOR Top Coat 75 Hardener – 3 kg pails

Shelf Life

Do not store product exposed to weather and sun. When kept in a cool, dry, protected area, sealed pails have a 12-month shelf life, but once opened may solidify within a few days.

Clean-up

Use MULTITEK Xylene or methylated spirits before curing. Exercise care when using solvent, review all Material Safety Data Sheet (MSDS) before use.

Health and Safety

In case of spills and accidents, refer to the MSDS of the products or when in doubt contact your local GCP representative.

Always wear protective clothing, gloves and protective goggles when handling chemical products.

For full information, consult the relevant MSDS.

Limitations

Information contained in this document does not cover all possible application scenarios or imply product suitability for an application. Please contact your local GCP representative or the GCP Technical Department for further information.

Warranties

GCP and contractors recognised by GCP as experienced in the application of GCP products will provide warranties for individual projects. Warranty periods offered are dependent on project details and complexity. Requests for very long warranty periods may necessitate increased membrane thicknesses to ensure longevity.

Contact your local GCP representative for further details.

Release Date: 28/10/2025. The information contained in this product data sheet supersedes all previous versions.

gcpat.com.au | Australia customer service: 1800 334 444 – anzorders@gcpat.com

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

EPOCOTE and SILCOR are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2025 GCP Applied Technologies, Inc. All rights reserved.

GCP Australia Pty. Ltd., 14 Colebard Street West, Archerfield, Brisbane, Queensland 4108, Australia

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Australia Pty. Ltd., 14 Colebard Street West, Archerfield, Brisbane, Queensland 4108, Australia

This document is only current as of the last updated date stated below and is valid only for use in Australia. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com.au. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2025-10-28

gcpat.com.au/solutions/products/silcor-liquid-waterproofing/silcor-top-coat-75